



Luxury Vinyl Tile  
**Technical Data Sheet**

Specification: 4.5mm, 24" x 24" TILE, 0.5mm / 20mil wear layer with Fibreglass  
 IIC Rating 50 STC Rating 54

Test Description	Test Standard	Result Grade - Test Data
Construction Installations		Commercial grade loose-lay or glue-down Luxury Vinyl Tile
Product finish		PU wear layer with ceramic beads and a UV coating / antimicrobial ingredient. Pore 2 emboss
Weight per carton		45.28lbs / 20.54kg's
Square foot per carton		27.13 s/f
Pieces per carton		7 pieces per carton
Reaction to fire	EN 13501-1+A1	Bfl-S1
Emission of formaldehyde	EN 717-1	Class E1
Slipperiness (Dynamic coefficient of friction)	EN 13893	DS
Wear resistance	EN 660-2:1999+A:2003 & EN 649:2011	Wear group T
TVOC	CDPH/EHLB Standard Method v1.2-2017 (California Section 01350)	Indoor Air Quality Certified to SCS-EC10.3-2014 v4.0
Flammability (Critical Radiant Flux)	ASTM E648-17a	Class I - 1.00 Watts/cm2
Flexibility	ASTM F137-08	No Breaks or Cracks
Chemical Resistance	ASTM F925	no change
Size & Squareness	ASTM F2421-05 (was utilized instead of ASTM F2055)	Pass - $\pm 0.016$ " per linear foot
Overall Thickness	ASTM F386-17	Pass - $\pm 0.005$ "
Wear Layer Thickness	ASTM F410-08	Pass
Dimensional Stability (after exposure to heat)	ASTM F2199	(-) 0.0039" Length, (-) 0.0037" Width
Residual & Short Term Indentation	ASTM F1914-17	Pass - Difference 0.018"
Static Load Limit (conducted at 1000 lb)	ASTM F970-17	Residual Indentation : 0.005"
Static Coefficient of Friction	ASTM D2047-11	Arithmetic Ave 0.80
Light Stability (after 400 hours)	ASTM F1515-15	1.00 $\Delta$ Delta E
Heat Stability	ASTM F1514-03	1.22 $\Delta$ Delta E
Floor Score Certification		Certified
Country of Manufacture		South Korea (ROK)



excelsiorflooring.com